LS L29K

SMARTLED® 0603

The innovative SMARTLED 0603 joins the successful family of TOPLED. Invested with the same high quality, its unique features are due to set new standards in product development and design, opening up new applications on a new scale.



Applications

Electronic Equipment

- White Goods

Features:

- Package: SMT package 0603, colorless diffused resin
- Chip technology: InGaAIP
- Typ. Radiation: 150°
- Color: λ_{dom} = 630 nm (• super red)
- Optical efficacy: 5 Im/W
- Corrosion Robustness Class: 3B
- Qualifications: The product qualification test plan is based on the guidelines of AEC-Q101-REV-C, Stress Test Qualification for Automotive Grade Discrete Semiconductors.
- ESD: 2 kV acc. to ANSI/ESDA/JEDEC JS-001 (HBM, Class 2)





Ordering Information

Туре	Luminous Intensity ¹⁾ I _F = 2 mA I _v	Ordering Code
LS L29K-G1H2-1	1.80 4.50 mcd	Q65110A1758
LS L29K-G1J2-1	1.80 7.10 mcd	Q65110A1757
LS L29K-H1J2-1	2.80 7.10 mcd	Q65110A1756



Maximum Ratings

Parameter	Symbol		Values
Operating Temperature	T _{op}	min.	-40 °C
		max.	100 °C
Storage Temperature	T _{stg}	min.	-40 °C
	5	max.	100 °C
Junction Temperature	T _j	max.	110 °C
Forward current	I _F	max.	20 mA
T _A = 25 °C	·		
Surge Current	I _{FS}	max.	100 mA
t ≤ 10 μs; D = 0.005 ; T _A = 25 °C			
Reverse voltage 2)	V _R	max.	12 V
T _A = 25 °C	IX.		
ESD withstand voltage	V _{ESD}		2 kV
acc. to ANSI/ESDA/JEDEC JS-001 (HBM, Class 2)	ESU		



Characteristics

 $I_{_{\rm F}}$ = 2 mA; $T_{_{\rm A}}$ = 25 °C

Parameter	Symbol	Values	
Peak Wavelength	$\lambda_{_{peak}}$	typ.	643 nm
Dominant Wavelength 3)	λ_{dom}	min.	624 nm
I _F = 2 mA	doni	typ.	630 nm
		max.	636 nm
Spectral Bandwidth at 50% I _{rel,max}	$\Delta\lambda$	typ.	16 nm
Viewing angle at 50% ${\rm I_v}$	2φ	typ.	160 °
Forward Voltage 4)	V _F	min.	1.70 V
I _F = 2 mA	·	typ.	1.80 V
		max.	2.20 V
Reverse current ²⁾	I _R	typ.	0.01 µA
$V_R = 12 V$		max.	10 µA
Temperature Coefficient of Peak Wavelength -10°C \leq T \leq 100°C	$TC_{_{\lambda peak}}$	typ.	0.14 nm / K
Temperature Coefficient of Dominant Wavelength -10°C \leq T \leq 100°C	$TC_{\lambda dom}$	typ.	0.05 nm / K
Temperature Coefficient of Forward Voltage -10°C \leq T \leq 100°C	TC_{VF}	typ.	-1.8 mV / K
Real thermal resistance junction/ambient ⁵⁾⁶⁾	$R_{thJA real}$	max.	500 K / W
Real thermal resistance junction/solderpoint ⁵⁾	$R_{thJS real}$	max.	310 K / W



Brightness Groups

Group	Luminous Intensity ¹⁾ I _F = 2 mA min. I _v	Luminous Intensity. ¹⁾ I _F = 2 mA max. I _v	Luminous Flux ⁷⁾ I _F = 2 mA typ. Φ _V
G1	1.80 mcd	2.24 mcd	8.10 mlm
G2	2.24 mcd	2.80 mcd	10.10 mlm
H1	2.80 mcd	3.55 mcd	12.70 mlm
H2	3.55 mcd	4.50 mcd	16.10 mlm
J1	4.50 mcd	5.60 mcd	20.20 mlm
J2	5.60 mcd	7.10 mcd	25.40 mlm




Group Name on Label

Example: G1-1BrightnessWavelengthG11




Relative Spectral Emission⁷⁾

 $I_{rel} = f(\lambda); I_{F} = 2 \text{ mA}; T_{A} = 25 \text{ }^{\circ}\text{C}$



Radiation Characteristics ⁷⁾

 $I_{rel} = f(\phi); T_A = 25 \ ^{\circ}C$






Forward current ⁷

 $I_{F} = f(V_{F}); T_{A} = 25 °C$

Relative Luminous Intensity 7), 8)


 $I_v/I_v(2 \text{ mA}) = f(I_F); T_A = 25 \text{ °C}$





Relative Luminous Intensity ⁷⁾


 $I_{v}/I_{v}(25 \text{ °C}) = f(T_{j}); I_{F} = 2 \text{ mA}$






Max. Permissible Forward Current

 $I_{F} = f(T)$




Permissible Pulse Handling Capability

 $I_{_{\rm F}}$ = f(t_{_{\rm p}}); D: Duty cycle; T_{_{\rm A}} = 25 °C




Permissible Pulse Handling Capability

 $I_{F} = f(t_{p})$; D: Duty cycle; $T_{A} = 85 \text{ °C}$






Dimensional Drawing⁹⁾




Approximate Weight.	1.0 mg
Package marking:	Cathode
Corrosion test:	Class: 3B Test condition: 40°C / 90 % RH / 15 ppm $\rm H_2S$ / 14 days (stricter than IEC 60068-2-43)



Recommended Solder Pad ⁹⁾



Recommended Solder Pad ⁹⁾




For superior solder joint connectivity results we recommend soldering under standard nitrogen atmosphere.



Reflow Soldering Profile

Product complies to MSL Level 2 acc. to JEDEC J-STD-020E




Profile Feature	ofile Feature Symbol Pb-Free (SnAgCu) Assembly		embly	Unit	
		Minimum	Recommendation	Maximum	
Ramp-up rate to preheat ^{*)} 25 °C to 150 °C			2	3	K/s
Time t _s T _{smin} to T _{smax}	t _s	60	100	120	S
Ramp-up rate to peak ^{*)} $T_{\rm Smax}$ to $T_{\rm P}$			2	3	K/s
Liquidus temperature	TL		217		°C
Time above liquidus temperature	t		80	100	S
Peak temperature	Τ _Ρ		245	260	°C
Time within 5 °C of the specified peak temperature T_P - 5 K	t _P	10	20	30	S
Ramp-down rate* T _P to 100 °C			3	6	K/s
Time 25 °C to T _P				480	S

All temperatures refer to the center of the package, measured on the top of the component

* slope calculation DT/Dt: Dt max. 5 s; fulfillment for the whole T-range




Taping ⁹⁾



OHAY1491



Tape and Reel ¹⁰⁾




Reel Dimensions


А	W	N _{min}	W ₁	$W_{2 \max}$	Pieces per PU
180 mm	8 + 0.3 / - 0.1 mm	60 mm	8.4 + 2 mm	14.4 mm	5000



Barcode-Product-Label (BPL)



Dry Packing Process and Materials ⁹⁾



Moisture-sensitive product is packed in a dry bag containing desiccant and a humidity card according JEDEC-STD-033.



Notes

The evaluation of eye safety occurs according to the standard IEC 62471:2006 (photo biological safety of lamps and lamp systems). Within the risk grouping system of this IEC standard, the device specified in this data sheet falls into the class **exempt group (exposure time 10000 s)**. Under real circumstances (for exposure time, conditions of the eye pupils, observation distance), it is assumed that no endangerment to the eye exists from these devices. As a matter of principle, however, it should be mentioned that intense light sources have a high secondary exposure potential due to their blinding effect. When looking at bright light sources (e.g. headlights), temporary reduction in visual acuity and afterimages can occur, leading to irritation, annoyance, visual impairment, and even accidents, depending on the situation.

Subcomponents of this device contain, in addition to other substances, metal filled materials including silver. Metal filled materials can be affected by environments that contain traces of aggressive substances. Therefore, we recommend that customers minimize device exposure to aggressive substances during storage, production, and use. Devices that showed visible discoloration when tested using the described tests above did show no performance deviations within failure limits during the stated test duration. Respective failure limits are described in the IEC60810.

For further application related information please visit www.osram-os.com/appnotes



Disclaimer

Attention please!

The information describes the type of component and shall not be considered as assured characteristics. Terms of delivery and rights to change design reserved. Due to technical requirements components may contain dangerous substances.

For information on the types in question please contact our Sales Organization.

If printed or downloaded, please find the latest version on the OSRAM OS website.

Packing

Please use the recycling operators known to you. We can also help you – get in touch with your nearest sales office. By agreement we will take packing material back, if it is sorted. You must bear the costs of transport. For packing material that is returned to us unsorted or which we are not obliged to accept, we shall have to invoice you for any costs incurred.

Product and functional safety devices/applications or medical devices/applications

OSRAM OS components are not developed, constructed or tested for the application as safety relevant component or for the application in medical devices.

OSRAM OS products are not qualified at module and system level for such application.

In case buyer – or customer supplied by buyer – considers using OSRAM OS components in product safety devices/applications or medical devices/applications, buyer and/or customer has to inform the local sales partner of OSRAM OS immediately and OSRAM OS and buyer and /or customer will analyze and coordinate the customer-specific request between OSRAM OS and buyer and/or customer.



Glossary

- ¹⁾ **Brightness:** Brightness values are measured during a current pulse of typically 25 ms, with an internal reproducibility of ± 8 % and an expanded uncertainty of ± 11 % (acc. to GUM with a coverage factor of k = 3).
- ²⁾ **Reverse Operation:** Reverse Operation of 10 hours is permissible in total. Continuous reverse operation is not allowed.
- ³⁾ **Wavelength:** The wavelength is measured at a current pulse of typically 25 ms, with an internal reproducibility of ±0.5 nm and an expanded uncertainty of ±1 nm (acc. to GUM with a coverage factor of k = 3).
- ⁴⁾ **Forward Voltage:** The forward voltage is measured during a current pulse of typically 8 ms, with an internal reproducibility of ± 0.05 V and an expanded uncertainty of ± 0.1 V (acc. to GUM with a coverage factor of k = 3).
- ⁵⁾ **Thermal Resistance:** Rth max is based on statistic values (6σ).
- ⁶⁾ **Thermal Resistance:** RthJA results from mounting on PC board FR 4 (pad size \geq 5 mm² per pad)
- ⁷⁾ Typical Values: Due to the special conditions of the manufacturing processes of semiconductor devices, the typical data or calculated correlations of technical parameters can only reflect statistical figures. These do not necessarily correspond to the actual parameters of each single product, which could differ from the typical data and calculated correlations or the typical characteristic line. If requested, e.g. because of technical improvements, these typ. data will be changed without any further notice.
- ⁸⁾ **Characteristic curve:** In the range where the line of the graph is broken, you must expect higher differences between single devices within one packing unit.
- ⁹⁾ **Tolerance of Measure:** Unless otherwise noted in drawing, tolerances are specified with ±0.1 and dimensions are specified in mm.
- ¹⁰⁾ **Tape and Reel:** All dimensions and tolerances are specified acc. IEC 60286-3 and specified in mm.




Revision History			
Version	Date	Change	
1.2	2020-03-18	Schematic Transportation Box Dimensions of Transportation Box Not for new design removed	



LS L29K

Published by OSRAM Opto Semiconductors GmbHEU RoHS and China RoHS compliant productLeibnizstraße 4, D-93055 Regensburg此产品符合欧盟 RoHS 指令的要求;





e